

Deformation of Fermi Surface Due to Antiferromagnetic Correlation

K. Morita ^{a,1}, K. Miyake ^a,

^a*Department of Physical Science,
Graduate School of Engineering Science, Osaka University,
Toyonaka, Osaka 560-8531, Japan*

Abstract

It is investigated, on the basis of the fluctuation exchange approximation, how the shape of the Fermi surface is modified in two-dimensional $t - t' - U$ Hubbard model at half filling as strength of the onsite Coulomb interaction U is increased. The antiferromagnetic (AF) correlation length is shown to be enhanced as the Coulomb interaction get closer to the critical value U_c for the onset AF order. At the same time, the shape of the renormalized Fermi surface is deformed showing the tendency of nesting near U_c .

Keywords:

FLEX, Antiferromagnetic correlation, $t - t' - U$ model,
Fermi surface

Layered cuprates have attracted much attention over the past decade because they exhibit anomalous behaviors in the normal state except for the fact that they have record high transition temperature (T_c). Some of the anomalous properties have features expressed by keywords, spin-charge separation aspect, spin-gap behavior, and so on [1–3]. They cannot be explained by the conventional Fermi liquid theory in its simple form. It is, however, expected that the Fermi surface of quasi particle becomes nearly nested near the antiferromagnetic (AF) insulator phase [4]. Then it has been shown that such anomalous properties can be understood as effects of AF spin fluctuations with technically nested Fermi surface [5,6]. Yanase-

Yamada calculated the one-particle self-energy on the one loop approximation using phenomenological form of the spectrum of magnetic excitations, and pointed out that the strong AF spin fluctuations works to deform the Fermi surface as to be nested [7]. This problem has also been studied in 2D Hubbard model on the square lattice by the self-consistent second order perturbation theory (SC-SOPT) [8], and in 2D Hubbard model on the triangular lattice by a simple second order perturbation [9]. These theories, however, cannot treat of spin fluctuations properly. Because of that, only a little tendency of change could be observed. The purpose of this paper is to study, on the basis of the fluctuation exchange (FLEX) approximation, how the shape of the Fermi surface is modified in two-dimensional $t - t' - U$ Hubbard model at half filling, which is one of the simplest model having features

¹ Corresponding author.
morita@eagle.mp.es.osaka-u.ac.jp

E-mail:

of layered high- T_c cuprates, as strength of U is increased. By adopting FLEX [10], we can take into account an effect of strong AF spin fluctuations.

The Green function and self-energy on the real axis are calculated by the standard method [11–13], and the Fermi surface and chemical potential are determined so as to satisfy the Luttinger sum rule [14]. We have retained 128×128 lattice points and 512 ($\equiv N$) discrete points of energy. Both of the cut-off value of energy ε_c and Matsubara frequency $\varepsilon_{nc} = (2N - 1)\pi T$ are $30t$ corresponding to the temperature $T/t = 0.0093$. A result of deformed Fermi surface is shown in Fig. 1 for the system with $U/t = 3.12$, $t'/t = 0.2$, t and t' being the transfer between the nearest neighbors and the second nearest neighbors. The AF correlation length ξ/a , a being the lattice constant, is estimated as $\xi/a = 14.8$ on FLEX approximation. The degree of deformation of the Fermi surface at the zone boundary $k_y = \pi$ is $\Delta k_x = -0.067 \pm 0.025$ and along the line $k_x = k_y$ is $\Delta k_\perp = 0.017 \pm 0.017$ for $U/t = 3.12$, where Δk is the difference between the Fermi wave number without interaction and the renormalized one. As we can see in Fig. 1, the Fermi surface is deformed in the direction to the nesting. The corresponding values of Δk for $U/t = 2$ is $\Delta k_x = -0.018 \pm 0.025$ and $\Delta k_\perp = 0.017 \pm 0.017$, which can hardly be seen if they are drawn as Fig. 1.

Deformation of the Fermi surface, calculated by SCSOPT in 2D Hubbard model near the half-filling, cannot be seen clearly even for rather large value of interaction $U/t = 4$ [8]. This is also the case in Ref [9]. On the other hand, change of the Fermi surface we calculated is not so large as that of Yanase-Yamada who claimed that much larger deformation is obtained even smaller value of $\xi/a = 6$ [7].

We acknowledge O. Narikiyo for fruitful discussions. One of us (K. Morita) is grateful to Y. Okuno and T. Takimoto for their useful comments and advice about a technique of numerical calculation. This work is supported by a Grant-in-Aid for COE Research (10CE2004) of Ministry of Education, Science, Sports and Culture.




Fig. 1. Deformation of Fermi surface. Solid line is for the Fermi surface without interaction, and dashed line for the renormalized Fermi surface.

References

- [1] H. Takagi, T. Ido, S. Ishibashi, M. Uota, S. Uchida, Y. Tokura, Phys. Rev. B **40** (1989) 2254.
- [2] See, e.g., M. A. Kastner *et al.*, Rev. Mod. Phys. **70** (1998) 897.
- [3] P. W. Anderson, Phys. Rev. Lett. **67** (1991) 2092.
- [4] K. Miyake, unpublished.
- [5] K. Miyake, O. Narikiyo, J. Phys. Soc. Jpn. **63** (1994) 2042.
- [6] K. Miyake, O. Narikiyo, J. Phys. Soc. Jpn. **63** (1994) 3821.
- [7] Y. Yanase, K. Yamada, J. Phys. Soc. Jpn. **68** (1999) 908.
- [8] H. Nojiri, J. Phys. Soc. Jpn. **68** (1999) 548.
- [9] S. Yoda, K. Yamada, to be published in Phys. Rev. B.
- [10] J. Clayhold, N. P. Ong, Z. Z. Wang, J. M. Tarascono, P. Barboux, Phys. Rev. B **39** (1989) 7324.
- [11] V. Zlatic, Phys. Rev. B **52** (1995) 3639.
- [12] F. Margio, M. Schossamann, J. P. Carbotte, Phys. Rev. B **37** (1988) 4965.
- [13] T. Hotta, J. Phys. Soc. Jpn. **64** (1995) 2923.
- [14] A. A. Abrikosov, L. P. Gorkov, I. Y. Dzyaloshinskii, Quantum Field Theoretical Methods in Statistical Physics (Pergamon Press, London, 1965).